

Procentowa zawartość substancji zawartych w poszczególnych typach baterii

system	METALE										ELEKTROLITY					NIEMETALE
	Pb	Ni	Cd	Zn	Mn	Ag	Hg	Li	Fe	H ₂ SO ₄	KOH	NH ₄ Cl ZnCl ₂	organ. elektr.	H ₂ O	plastik papier *	
Pb/PbO ₂	65	-	-	-	-	-	-	-	-	8	-	-	-	-	17	10
NiCd (stal c.)	-	20	15	-	-	-	-	-	45	-	5	-	-	-	10	5
Zn/ MnO ₂ - kwas - alkaliczne	-	-	-	20 20	25 30	-	-	-	20 20	-	-	5	-	-	10 10	20 15
Zn/AgO ₂	-	-	-	10	-	30	1	-	40	-	3	-	-	-	6	10
Zn/HgO	-	-	-	10	-	-	30	-	40	-	3	-	-	-	6	11
Zn/O ₂	-	-	-	30	-	-	2	-	45	-	4	-	-	-	8	10
Li/MnO ₂	-	-	-	-	30	-	-	2	50	-	-	-	10	-	-	10

* Oprócz tego węgiel, grafit, smołę, szkło, krzemionkę, papier, folię, wodór.